





Popierines str. 3, Jasiunai, Salcininkų raj. Lithuania +370 626 81 030 info@polinordic.com

UAB "Polivektris" www.polinordic.com All rights reserved.

POLILON-MONO

ABOUT PRODUCT

POLILON MONO is a premium quality extruded polycarbonate (PC) solid sheet with double sided UV-protection. This product has extremely high impact resistance, which makes it essentially unbreakable. **POLILON MONO** solid sheets is the ideal choice for applications where high optical clarity and impact resistance is required. It can be easily thermoformed and fabricated.

POLILON MONO offers the highest durability values of all thermoplastics and unparalleled design freedom, which conforms the most demanding applications.

APPLICATION

- Noise barriers for expressways, railways and urban elevated roads
- Wind shields
- Panels of advertising light boxes and
- Advertising display boards
- Medical equipment including eyewear and headgear
- Bridges

- The daylighting ceiling of buildings, skylights
- domes and sport arenas
- Security and anti-vandal glazing, safety
- screens and acoustic screens
- Industrial visors, googles and helmets
- Electronics
- Automotive and machinery parts and equipment

ADVANTAGES

- 200 times stronger than glass
- Highest impact resistance of all thermoplastics and good chemical resistance
- High clarity and light transmission
- Easily handled, machined and thermoformed
- Light weight (two times lighter than glass)
- Ideal for use as safety glazing or vandalism protection
- UV protected for improved longevity
- Excellent ink adhesion and print quality
- Excellent fire behavior, self-extinguishable, high tolerances for ambient temperature
- Nontoxic and environment friendly 100% recyclable



UAB "Polivektris"

POLILON-MONO

DELIVERY CONDITIONS

CHARACTERISTIC	UNIT	VALUE
Thickness	mm	From 1,5 up to 15
Width	mm	Up to 2050
Length	mm	30501
Color	-	Clear, any other color
Protective film	-	Transparent (both sides) ²

¹ Other lengths available

TECHNICAL SPECIFICATIONS

PROPERTIES	UNIT	VALUE
Density	g/cm³	1,20
Vicat softening temperature	°C	144
Moisture absorption	%	0,15
Light transmission	%	Up to 90
Tensile modulus	MPa	2300
Flexural strength	MPa	90
Nominal strain at break	%	60
Impact Resistance	Charpy unnotched	Non-break
	Charpy notched	35
	Izod notched	> 65
Coefficient of linear expansion	mm/m/°C	0,065



² Other films or prints available